
Barrier Film Metallised, Broad Seal, High Hot Tack & Barrier

HST-1(HSB) MO T095

Typical Values



Description

Structure

It is a co-extruded, one side metallised and other side low heat sealable & high hot tack Bi-axially Oriented Polypropylene film.

Features

- Excellent performance in VFFS & HFFS machine
- Good metal adhesion to film
- Very good barrier to moisture and light
- Very good gas barrier
- High heat seal strength
- High hot tack strength
- Broad seal range

Applications

As a laminate for snack food, bakery & confectionery packaging application

		lypicat values		
Properties	Ref.	Units	ASTM # / Test Method	HST-1(HSB)MO T095
		Physical Da	ta	
Average Thickness		micron	D-374-C	18
		gauge		72
		mils		0.7
Thickness Variation		% (<u>+</u>)		3
Density		g/cc		0.905
Average Substance		g/m²		16.3
Kinetic COF	UT-UT		D-1894	0.35 - 0.45
Yield		m²/kg	D - 4321	61.3
		in²/lb		43098
		Optical Dat	ta	
Optical Density			СТМ	2.2
		Mechanical D	ata	
Tensile Strength	MD	kg/ cm²	D-882	1300 -1500
	TD			2600 -2800
Elongation	MD	- %	D-882	150 -190
	TD			40 -70
		Thermal Da	ta	
Shrinkage (120°C/248°F, 5 min.)	MD	MD %	D-1204	3.0 - 5.0
	TD			1.0 - 3.0
Heat Seal Range		°C / °F	СТМ	95 - 145 / 203 - 293
Heat Seal Strength		g/25mm	СТМ	>500
Hot Tack Strength		g/30mm	115°C	395
		Barrier Dat	:a	
MVTR (38°C, 90%RH)		g/m²/day	F-1249	< 0.25
MVTR (100°F, 90%RH)		g/100in²/day		< 0.01
OTR (23 °C, 0%RH)		cc/m²/day	D-3985	< 30
OTR (74 °F, 0%RH)		cc/100in²/day		< 1.93

CTM : Cosmo Test Method MD : Machine Direction TD : Transverse Direction LTS: low temperature sealing UT = Un-treated Disclaimer : The information provided above is based on COSMO FILMS LTD's conclusive tests, which are indicative only and provided as guidelines. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.

Cosmo Films Limited